

Aalto Trade Exterior Low Sheen

Product	Aalto Trade Exterior Low Sheen AT302	
Description	Aalto Trade Exterior Low Sheen is a professional quality waterbased paint in a low sheen finish for exterior surfaces. Provides exceptional performance on most common exterior substrates, including weatherboards, timber, concrete and galvanised iron.	
Guarantee	Aalto Trade Exterior Low Sheen comes with a 10 year guarantee. For details, visit www.aaltopaint.co.nz	
Typical Uses	May be used on suitably prepared: <ul style="list-style-type: none"> - Weatherboards - Timber - HardieFlex™ - Concrete and concrete blocks - Textured surfaces - Galvanised iron, Colorsteel® - Fibre cement products 	
Physical Properties	Binder type	100% acrylic
	Solvent	Water
	Colour	White and tinted colours
	Finish	Low sheen – 10% gloss
	Dry time	30 minutes at 20°C
	Recoat time	2 hours at 20°C
	Number of coats	2
	Theoretical coverage	10-12m ² per litre
	Rec. film thickness	100 microns per coat, WFT
	Thinning and clean up	Water
Preparation	Ensure surfaces are free from loose and flaking paint. Wash surfaces with a suitable exterior cleaner prior to painting to remove dirt, oils, grease and other contaminants. Where there has been mould, treat the area with a moss and mould remover.	
Application	Aalto Trade Exterior Low Sheen can be applied by synthetic brush, roller, or spray. Airless spray – a 415 or 417 tip is recommended for weatherboards, and a 517 tip is recommended for textured surfaces before being back-rolled.	
	Weatherboards – pre-primed	
	1. Apply 2 coats of Aalto Trade Exterior Low Sheen, allowing 2 hours between coats	
	New timber	
	1. Apply 1 coat of Aalto 3 in 1 Undercoat	
	2. Apply 2 coats of Aalto Trade Exterior Low Sheen, allowing 2 hours between coats	
	Repaints	
	1. Sand existing paint work and spot prime bare timber with Aalto 3 in 1 Undercoat	
	2. Apply 2 coats of Aalto Trade Exterior Low Sheen, allowing 2 hours between coats	

aalto

Concrete block, reinforced concrete

1. Where porous, seal with Aalto 3 in 1 Undercoat thinned 50% with water
2. Apply 1 coat of Aalto 3 in 1 Undercoat unthinned
3. Apply 2 coats of Aalto Trade Exterior Low Sheen, allowing 2 hours between coats

Fibre cement

1. Seal with Aalto Trade Exterior Low Sheen thinned 20% with water
2. Apply 2 coats of Aalto Trade Exterior Low Sheen, allowing 2 hours between coats

Galvanised iron

1. Treat rusty areas with an appropriate preparation solution
2. Apply 1 coat of Procoat Oil Based Galvanised Iron Primer
3. Apply 2 coats of Aalto Trade Exterior Low Sheen, allowing 2 hours between coats

Maintenance

Maintain your exterior paint surface by washing it every 12 months (after each winter is a great time), with a suitable exterior cleaner to remove dirt deposits. We do not recommend the use of bleach as this can affect the appearance of the colour over time. Dirt, salt, and bird deposits left on the paint surface will encourage the growth of mould, and affect the paints performance.

Performance and Limitations**Performance**

- Excellent durability and gloss retention
- Excellent intercoat adhesion
- Excellent flexibility
- Resists dirt pick-up

Limitations

- Should not be applied if temperatures are below 10°C or when it is liable to drop below 10°C during the drying period
- Dry time may be impeded if the relative humidity is high
- Should not be used on closing surfaces around doors and windows

Health and Safety

For detailed health and safety information refer to Material Safety Datasheet (MSDS)

Usage

- Provide adequate ventilation during use
- Keep out of reach of children

Personal

- Avoid contact with skin and eyes
- Wash hands after use

Protective equipment

- Wear protective eyewear and waterproof gloves
- When spraying, wear dust mask or suitable respirator

Storage

- Store away from direct sunlight

Health Effects

If poisoning occurs, contact a doctor or Poisons Information Centre (NZ 0800 764 766).

If swallowed: Rinse mouth with water. Do NOT induce vomiting. Give a glass of water.

Eyes: If in eyes, hold eyes open, flush with running water for at least 15 minutes,

Skin: If skin contact occurs, remove contaminated clothing and wash skin thoroughly.

Inhaled: Remove from contaminated area.

aalto

Spills and Disposal

Do not allow spilt material to enter drains or other watercourses. Absorb spills with sand or other inert material. Do not pour leftover paint down the drain. Unwanted paint should be kept in a sealed container, such as an empty paint can, and disposed of via special waste collection services. Check with your local council regarding the disposal of empty paint containers. Empty paint containers should be left open in a well-ventilated area to dry out. When dry, recycle steel containers via steel can recycling programs. Disposal of empty paint containers via domestic recycling programs may vary between local authorities.

aalto