

## Aalto Ultra Premium Exterior Flexibuild

Product	Aalto Ultra Premium Exterior Flexibuild AA304																				
Description	Aalto Ultra Premium Exterior Flexibuild is a premium waterbased paint in a satin finish designed for repainting plaster homes. The unique high build formulation allows the paint to be applied at twice the normal thickness, bridging fine hairline cracks in aged plaster, and providing a beautiful and durable protective coating.																				
Guarantee	Aalto Ultra Premium Exterior Flexibuild paint comes with a 15 year guarantee. For details, visit <a href="http://www.aaltopaint.co.nz">www.aaltopaint.co.nz</a>																				
Typical Uses	May be used on suitably prepared: <ul style="list-style-type: none"><li>– Exterior thin film plaster</li><li>– Solid plaster</li><li>– Concrete block</li></ul>																				
Physical Properties	<table><tr><td>Binder type</td><td>100% acrylic</td></tr><tr><td>Solvent</td><td>Water</td></tr><tr><td>Colour</td><td>White and tinted colours</td></tr><tr><td>Finish</td><td>Satin – 20% gloss</td></tr><tr><td>Dry time</td><td>40 minutes at 20°C</td></tr><tr><td>Recoat time</td><td>4 hours at 20°C</td></tr><tr><td>Number of coats</td><td>2 or 3 (see application details below)</td></tr><tr><td>Theoretical coverage</td><td>6-8m<sup>2</sup> per litre</td></tr><tr><td>Rec. film thickness</td><td>120-150 microns per coat, WFT</td></tr><tr><td>Thinning and clean up</td><td>Water</td></tr></table>	Binder type	100% acrylic	Solvent	Water	Colour	White and tinted colours	Finish	Satin – 20% gloss	Dry time	40 minutes at 20°C	Recoat time	4 hours at 20°C	Number of coats	2 or 3 (see application details below)	Theoretical coverage	6-8m <sup>2</sup> per litre	Rec. film thickness	120-150 microns per coat, WFT	Thinning and clean up	Water
Binder type	100% acrylic																				
Solvent	Water																				
Colour	White and tinted colours																				
Finish	Satin – 20% gloss																				
Dry time	40 minutes at 20°C																				
Recoat time	4 hours at 20°C																				
Number of coats	2 or 3 (see application details below)																				
Theoretical coverage	6-8m <sup>2</sup> per litre																				
Rec. film thickness	120-150 microns per coat, WFT																				
Thinning and clean up	Water																				
Preparation	Ensure surfaces are free from loose and flaking paint. Wash surfaces with a suitable exterior cleaner prior to painting to remove dirt, oils, grease and other contaminants. Where there has been mould, treat the area with a moss and mould remover.																				
Application	<p>Aalto Ultra Premium Exterior Flexibuild can be applied by synthetic brush, roller, or spray. Airless spray – a 523 tip or larger is recommended due to the fibres in the paint, and a coarse filter should be used.</p> <p>Exterior plaster – previously painted, fine hairline cracks</p> <ol style="list-style-type: none"><li>1. Apply 2 coats of Aalto Ultra Premium Exterior Flexibuild, allowing 4 hours between coats</li></ol> <p>Exterior plaster – previously painted, large hairline cracks</p> <ol style="list-style-type: none"><li>1. Fill any cracks larger than 2mm with a suitable exterior paintable filler</li><li>2. Apply 1 coat of a flexible membrane coating at a spread rate of 2m<sup>2</sup> per litre</li><li>3. Apply 2 coats of Aalto Premium Exterior Flexibuild, allowing 4 hours between coats</li></ol> <p>Exterior plaster – new and unpainted</p> <ol style="list-style-type: none"><li>1. Apply 1 coat of a flexible membrane coating at a spread rate of 2m<sup>2</sup> per litre</li><li>2. Apply 2 coats of Aalto Ultra Premium Exterior Flexibuild, allowing 4 hours between coats</li></ol> <p>Fibre cement, concrete slab, concrete brick</p> <ol style="list-style-type: none"><li>1. Apply 2 coats of Aalto Ultra Premium Exterior Flexibuild, allowing 4 hours between coats</li></ol>																				

# aalto

Maintenance	Maintain your exterior paint surface by washing it every 12 months (after each winter is a great time), with a suitable exterior cleaner to remove dirt deposits. We do not recommend the use of bleach as this can affect the appearance of the colour over time. Dirt, salt, and bird deposits left on the paint surface will encourage the growth of mould, and affect the paints performance.
Performance and Limitations	<p>Performance</p> <ul style="list-style-type: none"><li>– Excellent durability and gloss retention</li><li>– Excellent flexibility</li><li>– Resists dirt pick-up</li></ul> <p>Limitations</p> <ul style="list-style-type: none"><li>– Large hairline cracks must be repaired with a suitable exterior flexible and paintable filler</li><li>– Satin finish – may be overcoated with Aalto Ultra Premium Exterior Gloss or Low Sheen if a different sheen level is required</li><li>– Should not be applied if temperatures are below 5°C or when it is liable to drop below 5°C during the drying period</li></ul>
Health and Safety	<p>For detailed health and safety information refer to Material Safety Datasheet (MSDS)</p> <p>Usage</p> <ul style="list-style-type: none"><li>– Provide adequate ventilation during use</li><li>– Keep out of reach of children</li></ul> <p>Personal</p> <ul style="list-style-type: none"><li>– Avoid contact with skin and eyes</li><li>– Wash hands after use</li></ul> <p>Protective equipment</p> <ul style="list-style-type: none"><li>– Wear protective eyewear and waterproof gloves</li><li>– When spraying, wear dust mask or suitable respirator</li></ul> <p>Storage</p> <ul style="list-style-type: none"><li>– Store away from direct sunlight</li></ul>
Health Effects	<p>If poisoning occurs, contact a doctor or Poisons Information Centre (NZ 0800 764 766).</p> <p>If swallowed: Rinse mouth with water. Do NOT induce vomiting. Give a glass of water.</p> <p>Eyes: If in eyes, hold eyes open, flush with running water for at least 15 minutes,</p> <p>Skin: If skin contact occurs, remove contaminated clothing and wash skin thoroughly.</p> <p>Inhaled: Remove from contaminated area.</p>
Spills and Disposal	Do not allow spilt material to enter drains or other watercourses. Absorb spills with sand or other inert material. Do not pour leftover paint down the drain. Unwanted paint should be kept in a sealed container, such as an empty paint can, and disposed of via special waste collection services. Check with your local council regarding the disposal of empty paint containers. Empty paint containers should be left open in a well-ventilated area to dry out. When dry, recycle steel containers via steel can recycling programs. Disposal of empty paint containers via domestic recycling programs may vary between local authorities.

# aalto