

aaltopaint

WB Exterior

Exterior Gloss, Satin, Low Sheen

Product Line Aalto WB Exterior Gloss, Satin and Low Sheen
AA305-306-307

Description Aalto WB Exterior paint is an ultra premium waterbased and self priming paint for exterior surfaces. This reinforced acrylic paint has been formulated to provide a washable and UV resistant finish to common exterior substrates including weatherboards, timber, concrete and galvanised iron.

Guarantee Aalto WB Exterior paint comes with a 15 year guarantee.
For details, visit www.aaltopaint.co.nz

Typical Uses May be used on suitably prepared:

- Weatherboards
- Colorsteel®
- Timber
- Hardiflex®
- Plywood
- Galvanised iron
- Steel
- Fibre cement products
- Concrete/concrete blocks
- Zinalume

Properties

Binder type	100% acrylic
Solvent	Water
Colour	White and tinted colours
Finish	Gloss: 70% gloss Satin: 20% gloss Low sheen: 10% gloss
Dry time	30 minutes at 20°C
Recoat time	2 hours at 20°C
Number of coats	2 or 3 (see application details below)
Theoretical coverage	12-14m ² per litre
Recommended film thickness	100 microns per coat WFT
Thinning/clean up	Water

Preparation Ensure surfaces are free from loose and flaking paint. Wash surfaces with a suitable exterior cleaner prior to painting to remove any oil, grease, dirt, mould or other contaminants.

Application

Aalto WB Exterior paint may be applied by synthetic brush, roller or spray. Airless spray – a 415 or 417 tip is recommended for weatherboards and smooth surfaces, and a 517 tip is recommended for textured surfaces, followed by back rolling.

Weatherboards (pre-primed)

1. Apply 2 coats of Aalto WB Exterior in selected gloss level, allowing 2 hours between coats

New Timber

1. Apply 1 coat of Aalto WB Trade 3 in 1 Undercoat, allow 2 hours to dry
2. Apply 2 coats of Aalto WB Exterior in selected gloss level, allowing 2 hours between coats

Repaints

1. Sand existing paint work and spot prime bare timber with Aalto WB Trade 3 in 1 Undercoat
2. Apply 2 coats of Aalto WB Exterior in selected gloss level, allowing 2 hours between coats

Concrete Block

1. Where porous, seal with Aalto WB Trade 3 in 1 Undercoat thinned with water 50/50
2. Apply 1 coat of Aalto WB Trade 3 in 1 Undercoat (not thinned)
3. Apply 2 coats of Aalto WB Exterior in selected gloss level, allowing 2 hours between coats

Fibre Cement, Concrete Slab, Concrete Tiles, Bricks

1. Seal with Aalto WB Trade 3 in 1 Undercoat
2. Apply 2 coats of Aalto WB Exterior in selected gloss level, allowing 2 hours between coats

Galvanised Iron

1. Treat rusty areas with an appropriate preparation solution
2. Apply 1 coat of oil based galvanised iron primer
3. Apply 2 coats of Aalto WB Exterior in selected gloss level, allowing 2 hours between coats

Performance & Limitations

Performance

- Excellent durability and gloss retention
- Exceptional intercoat adhesion
- Excellent flexibility
- Resists dirt pick-up
- Suitable for the collection of drinking water

Limitations

- When applying over cedar or highly treated timber where severe stain bleeding may occur, seal with Aalto WB Trade 3 in 1 Undercoat before applying 2 coats of Aalto WB Exterior in selected gloss level
- Should not be used on closing surfaces around doors or windows
- Aalto WB Exterior Gloss is not recommended for decks or walked on areas

- Should not be applied in temperatures under 5°C
- Dry time may be impeded if the relative humidity is high

Health & Safety

For detailed health and safety information refer to material safety data sheet (MSDS).

Usage

- Provide adequate ventilation during use
- Keep out of reach of children

Personal

- Avoid contact with skin and eyes
- Wash hands after use

Protective Equipment

- Wear eye protection and waterproof gloves
- When spraying, wear dust mask or suitable respirator

Storage

- Store away from direct sunlight

Health Effects

If poisoning occurs, contact a Doctor or Poisons Information Centre (NZ 0800 764 766).

Swallowed: Rinse mouth with water. If swallowed, do NOT induce vomiting. Give a glass of water.

Eyes: If in eyes, hold eyes open, flush with running water for at least 15 minutes.

Skin: If skin contact occurs, remove contaminated clothing and wash skin thoroughly.

Inhaled: Remove from contaminated area.

Spills & Disposal

Do not allow spilt material to enter drains or other watercourses. Absorb spills with sand or other inert material. Do not pour leftover paint down the drain.

Unwanted paint should be kept in a sealed container, such as an empty paint can, and disposed of via special waste collection services. Check with your local Council regarding the disposal of empty paint containers. Empty paint containers should be left open in a well-ventilated area to dry out. When dry, recycle steel containers via steel can recycling programs. Disposal of empty paint containers via domestic recycling programs may vary between local authorities.

Avoid freezing or temperatures in excess of 50°C