

aaltopaint

WB Trade Exterior

Exterior Semi Gloss, Low Sheen

Product Line Aalto WB Trade Exterior
AT301-302

Description Aalto WB Trade Exterior is a professional quality waterbased paint for exterior surfaces. Provides exceptional performance on most common exterior substrates including weatherboards, timber, concrete and galvanised iron.

Guarantee Aalto WB Trade Exterior comes with a 10 year guarantee.
For details, visit www.aaltopaint.co.nz

Typical Uses May be used on suitably prepared:

- Weatherboards
- Timber
- Hardiflex
- Concrete and concrete blocks
- Textured surfaces
- Galvanised iron
- Fibre cement products

Properties

| | |
|----------------------------|---|
| Binder type | 100% acrylic |
| Solvent | Water |
| Colour | White and tinted colours |
| Finish | Semi gloss: 35% gloss Low sheen: 10% gloss |
| Dry time | 30 minutes at 20°C |
| Recoat time | 2 hours at 20°C |
| Number of coats | 2 |
| Theoretical coverage | 10-12m ² per litre |
| Recommended film thickness | 100 microns per coat WFT |
| Thinning/clean up | Water |

Preparation Ensure surfaces are free from loose and flaking paint. Wash surfaces with a suitable exterior cleaner prior to painting to remove any oil, grease, dirt, mould or other contaminants.

Application

Aalto WB Trade Exterior may be applied by synthetic brush, roller or spray. Airless spray – a 415 or 417 tip is recommended for weatherboards, and a 517 tip is recommended for textured surfaces before being back-rolled.

Weatherboards (pre-primed)

1. Apply 2 coats of Aalto WB Trade Exterior in selected gloss level, allowing 2 hours between coats

New Timber

1. Apply 1 coat of Aalto WB Trade 3 in 1 Undercoat, allow 2 hours to dry
2. Apply 2 coats of Aalto WB Trade Exterior in selected gloss level, allowing 2 hours between coats

Repaints

1. Sand existing paint work and spot prime bare timber with Aalto WB Trade 3 in 1 Undercoat
2. Apply 2 coats of Aalto WB Trade Exterior in selected gloss level, allowing 2 hours between coats

Concrete Block, Reinforced Concrete

1. Where porous, seal with Aalto WB Trade 3 in 1 Undercoat thinned with water 50/50
2. Apply 1 coat of Aalto WB Trade 3 in 1 Undercoat (not thinned)
3. Apply 2 coats of Aalto WB Trade Exterior in selected gloss level, allowing 2 hours between coats

Fibre Cement

1. Seal with Aalto WB Trade Exterior thinned 20% with water
2. Apply 2 coats of Aalto WB Trade Exterior in selected gloss level, allowing 2 hours between coats

Galvanised Iron

1. Treat rusty areas with an appropriate preparation solution
2. Apply 1 coat of Procoat Oil Based Galvanised Iron Primer
3. Apply 2 coats of Aalto WB Trade Exterior in selected gloss level, allowing 2 hours between coats

Performance & Limitations

Performance

- Excellent durability and gloss retention
- Exceptional intercoat adhesion
- Excellent flexibility
- Resists dirt pick-up

Limitations

- Should not be used on closing surfaces around doors or windows
- Should not be applied if temperatures are below 10°C or when it is liable to drop below 10°C during drying period
- Dry time may be impeded if the relative humidity is high

Health & Safety

For detailed health and safety information refer to material safety data sheet (MSDS).

Usage

- Provide adequate ventilation during use
- Keep out of reach of children

Personal

- Avoid contact with skin and eyes
- Wash hands after use

Protective Equipment

- Wear eye protection and waterproof gloves
- When spraying, wear dust mask or suitable respirator

Storage

- Store away from direct sunlight

Health Effects

If poisoning occurs, contact a Doctor or Poisons Information Centre (NZ 0800 764 766).

Swallowed: Rinse mouth with water. If swallowed, do NOT induce vomiting. Give a glass of water.

Eyes: If in eyes, hold eyes open, flush with running water for at least 15 minutes.

Skin: If skin contact occurs, remove contaminated clothing and wash skin thoroughly.

Inhaled: Remove from contaminated area.

Spills & Disposal

Do not allow spilt material to enter drains or other watercourses. Absorb spills with sand or other inert material. Do not pour leftover paint down the drain.

Unwanted paint should be kept in a sealed container, such as an empty paint can, and disposed of via special waste collection services. Check with your local Council regarding the disposal of empty paint containers. Empty paint containers should be left open in a well-ventilated area to dry out. When dry, recycle steel containers via steel can recycling programs. Disposal of empty paint containers via domestic recycling programs may vary between local authorities.